

BLANK PAGE



IS: 6579 - 1981 (Reaffirmed 2008)

Indian Standard SPECIFICATION FOR COARSE AGGREGATE FOR WATER BOUND MACADAM (First Revision)

Third Reprint JULY 1999

UDC 666.972.123:625.863.2

© Copyright 1981

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

Indian Standard

SPECIFICATION FOR COARSE AGGREGATE FOR WATER **BOUND MACADAM**

(First Revision)

Stones Sectional Committee, BDC 6

Chairman

SHRIB. RAMACHANDRAN

Robresonting

Geological Survey of India

Members

SHRI S. R. PRADHAN (Alternate to Shri B. Ramachandran)

Builders' Association of India SHRIK, K. AGRAWALA

SHRI K. K. MADHOR (Alternate) National Test House, Calcutta

Shri S. K. Banerjee SHRI P. R. DAS (Alternate)

SHBI R. K. BANSAL SHRI J. K. CHABAN

SHRIK. KAMLANATHAM (Alternate)

CHIEF ABORITECT CHIEF ENGINEER (B&R)

SHRIY. N. DAVE

Delhi Marble Dealers' Association, New Delhi

Engineer-in-Chief's Branch (Ministry of Defence)

Central Public Works Department, New Delhi Public Works Department, Government Rajasthan, Jaipur Department of Geology & Mining, Government of

Rajasthan, Udaipur

SHRI R. G. GUPTA (Alternate) DEPUTY DIRECTOR (RESEARCH), Public Works Department, Government of Utile PWD RESEARCH INSTITUTE. Pradesh, Lucknow

LUCKNOW

DR M. P. DHIR DR N. B. LAL (Alternate) DIRECTOR (CSMRS)

DEPUTY DIRECTOR (CSMRS) (Alternate)

DIRECTOR, GERI, VADODABA

SHRI M. K. GUPTA DR TOBAL ALI

Central Road Research Institute, New Delhi

Central Water Commission, New Delhi

Public Works Department, Government of Gujarat. Vadodara

Himalayan Tiles and Marble Pvt Ltd, Bombay

Engineering Research Laboratories, Government of Andhra Pradesh, Hyderabad

SHRI G. RAMARBISHNA (Alternate)

(Continued on page 2)

Copyright 1981

BUREAU OF INDIAN STANDARDS

This publication is protected under the Indian Copyright Act (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

18:6579 - 1981

(Continued from page 1)

Members

SHRIR. C. JAIN

DR A. K. LAHIBI SHEI K. VIKRAM (Alternate)

SERI R. G. LIMAYE DR G. S. MERROTRA

DR DINESH CHANDRA (Alternate)

SHEI PREM SWARUP

Representing

Ministry of Shipping & Transport (Roads Wing). New Delhi

Rajasthan State Granites and Marble Ltd. Jodhpur

Indian Institute of Technology, Bombay Central Building Research Institute, Roorkee

Department of Geology & Mining, Government of Uttar Pradesh, Lucknow

SHRI A. K. AGARWAL (Alternate) Da A, V. R. RAO

SHRI J. SEN GUPTA (Alternate RESEARCH OFFICER, MERI,

NASIK SUPERINTENDING ENGINEER

(DESIGNS) SUPERINTENDING ENGINEER

(DESIGNS) DEPUTY CHIEF ENGINEER

(I&D) (Alternate) SUPERINTENDING ENGINEER (PLANNING CIRCLE)

SHEI G. RAMAN, Director (Civ Engg) National Buildings Organization, New Delhi

Irrigation & Power Department, Government of Maharashtra, Bombay Public Works & Electricity Department, Govern-

ment of Karnataka, Bangalore

Public Works Department, Government Tamil Nadu, Madras

Public Works Department, Government of West Bengal, Calcutta Director General, ISI (Ex-officio Momber)

Secretary

SHRI S. SENGUPTA Assistant Director (Civ Engg), ISI

AMENDMENT NO. 1 OCTOBER 1996 TO

IS 6595 (Part 1): 1993 HORIZONTAL CENTRIFUGAL PUMPS FOR CLEAR, COLD WATER

PART 1 AGRICULTURAL AND RURAL WATER SUPPLY PURPOSES — SPECIFICATION

(Second Revision)

[Page 2, clause 8.1(a)] — Substitute the following for the existing matter:

'a) The pump shall be capable to operate without overloading the prime-mover in the specified head range. However, the head range shall be not less than minimum +5 percent and minimum -15 percent of rated duty point head up to 20 m. Above 20 m duty point head, the prime-mover shall not overload between duty point and minimum -3 m head.'

(HMD	20)

Reprography Unit, BIS, New Delhi, India

AMENDMENT NO. 2 OCTOBER 2000 TO

IS 6595 (PART 1): 1993 HORIZONTAL CENTRIFUGAL PUMPS FOR CLEAR. COLD WATER

PART 1 AGRICULTURAL AND RURAL WATER SUPPLY PURPOSES — SPECIFICATION

(Second Revision)

(Page 3, Fig. 1) — Insert the following Note:

'NOTE — Efficiency of the pumps having declared duty point beyond the efficiency lines on either side may be declared by the manufacturer and applicable tolerance applied. Where the point lies in between the efficiency lines, the higher value be taken as minimum efficiency.'

(Page 4, Fig. 2) — Insert the following Note:

NOTE — Efficiency of the pumps having declared duty point beyond the efficiency lines on either side may be declared by the manufacturer and applicable tolerance applied. Where the point lies in between the efficiency lines, the higher value be taken as minimum efficiency.

(ME 20)

Reprography Unit, BIS, New Delhi, India

Indian Standard

SPECIFICATION FOR COARSE AGGREGATE FOR WATER BOUND MACADAM

(First Revision)

0: FOREWORD

- 0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 27 February 1981, after the draft finalized by the Stones Sectional Committee had been approved by the Civil Engineering Division Council.
- 0.2 Water bound macadam (WBM) is a common item for highway construction. The coarse aggregates, accounting for nearly three-fourths of the volume and mass of WBM, may be said to be the main constituent. Many a time, an engineer-in-charge is faced with the problem of selecting the coarse aggregate for WBM from several alternative materials available. If the minimum physical requirements of such aggregates could be indicated, selection of the appropriate material would be easy. With this aspect in view, this standard has been prepared to lay down the requirements of coarse aggregates for WBM construction.
- 0.2.1 This standard was first published in 1972. It is being revised to incorporate improvements found necessary in the light of the usage of the standard and the suggestions made by various bodies implementing it. In this revision, a number of changes have been incorporated, the most important being the adoption of the WBM aggregates for construction of sub-base course also. The requirement of abrasion value, impact value and flakiness index of such aggregates for use as sub-base has been added and the size and grading of the WBM aggregates modified, depending on the sieve designation of IS: 460 (Part I)-1978*. A requirement for water absorption has also been included.
- 0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960†. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

^{*}Specification for test sieves: Part I Wire cloth test sieves (second revision). †Rules for rounding off numerical values (revised).

18: 6579 - 1981

i. SCOPE

1.1 This standard specifies the quality, physical properties and grading of coarse aggregates suitable for use in WBM construction.

2. MATERIALS

- 2.1 The coarse aggregates used for WBM construction shall be any one of the following:
 - a) Crushed or broken rock.
 - b) Crushed or broken slag, and
 - c) Broken brick aggregate.
- 2.1.1 Natural aggregates (like KANKAR, laterite, etc.) other than mentioned in 2.1 may also be used.

3. QUALITY

- 3.1 The coarse aggregates from natural sources shall be hard and durable. They shall be free from excessive flat, elongated, soft or disintegrated particles, dirt and other similar sources of weakness.
- 3.2 The coarse aggregates of slag shall be made from air-cooled blast furnace slag and shall not contain glassy material exceeding 20 percent and shall not weigh less than 1 120 kg/m². They shall be dense, of angular shape and shall be free from dirt and other similar sources of weakness.
- 3.3 The broken brick aggregate shall be made out of well burnt bricks (see IS: 1077-1976*). It shall be free from underburnt particles, dust and other foreign matter.

4. SIZE AND GRADING

4.1 The size and grading of the coarse aggregates shall be as specified in Table 1.

5. PHYSICAL REQUIREMENTS

5.1 Abrasion (Los Angeles) Value — The abrasion value of the coarse aggregates when tested in accordance with the method laid down in IS: 2386 (Part IV)-1963† shall not be more than 40 percent for wearing surface, 50 percent for base course and 60 percent for sub-base course.

^{*}Specification for common burnt clay building bricks (third revision), †Methods of test for aggregates for concrete: Part IV Mechanical properties,

TABLE 1 SIZE AND GRADING OF COARSE AGGREGATES (Clause 4.1)

Grading No.	Sieve Designation [see IS: 460 (Part I)-1978*]	Percentage Passing the Sieve by Mass	
(1)	(2)	(3)	
	mm		
1	106 75 63 37•5 19	100 55 to 80 25 to 60 0 to 15 0 to 5	
2	75 63 53 97-5 19	100 90 to 100 50 to 80 0 to 15 0 to 5	
3	63 53 37·5 19 11·2	100 95 to 100 30 to 65 0 to 10 0 to 5	

NOTE - For coarse aggregates susceptible to degradation during rolling, the above grading may not hold good.

5.2 Flakiness Index - The flakiness index of the coarse aggregates when tested in accordance with the method given in IS: 2386 (Part I)-1963* shall not be more than 15 percent. The flakiness index may be judiciously adjusted when the material is to be used in sub-base or when significant degradation is expected under rolling.

NOTE - The requirement of flakiness index shall be enforced only in the case of crushed broken stone and crushed slag.

5.3 Impact Value - The impact value of the aggregates when determined in accordance with the method given in IS: 2386 (Part IV)-1963† and IS: 5640-1970‡ shall not be more than 30 for wearing surface. 40 for base course and 50 for sub-base course.

NOTE - Aggregates like brick, KANKAR and laterite shall be tested for impact value under wet condition in accordance with the methods given in IS: 5640-19701.

^{*}Specification for test sieves: Part I Wire cloth test sieves (second revision).

^{*}Methods of test for aggregates for concrete: Part I Particle size and shape, †Methods of test for aggregates for concrete: Part IV Mechanical properties,

tMethods of test for determining aggregates impact value of soft coarse aggregates.

- 5.4 Water Absorption The water absorption of the aggregates when tested in accordance with the method given in IS: 2386 (Part III)-1963* shall not be more than 1.5 percent for wearing surface, base and sub-base course in the areas where the aggregates are subjected to freezing and thawing and shall not be more than 2 percent in other areas.
- 5.5 Soundness The soundness of the aggregates when tested in accordance with the method given in IS: 2386 (Part V)-1963† shall satisfy the following requirements:
 - a) Loss with sodium sulphate (5 cycles): 20 percent Max
 - b) Loss with magnesium sulphate (5 cycles): 30 percent Max

Norz — The aggregate shall be tested for soundness only when it has to undergo alternate freezing and thawing.

6. SAMPLING AND CRITERIA FOR CONFORMITY

6.1 The procedure of sampling and the criteria for conformity shall be as given in IS: 2430-1969‡.

7. SUPPLIER'S CERTIFICATE AND COST OF TESTS

- 7.1 The supplier shall satisfy himself that the material supplied conforms to the requirements of this standard and, if requested, shall furnish a certificate to this effect to the purchaser or his representative.
- 7.2 If the purchaser or his representative requires independent tests to be made, the sample for such tests shall be taken before or immediately after delivery at the option of the purchaser or his representative, and the tests shall be carried out in accordance with this standard and on the written instructions of the purchaser or his representative.
- 7.3 The supplier shall supply, free of charge, the material required for tests.
- 7.4 The cost of the tests carried out under 7,2 shall be borne as follows:
 - a) By the supplier, if the results show that the material does not comply with this standard; and
 - b) By the purchaser, if the results show that the material complies with this standard.

^{*}Methods of test for aggregates for concrete: Part III Specific gravity, density, voids, absorption and bulking.

[†]Methods of test for aggregates for concrete: Part V Soundness.

Methods for sampling of aggregates for concrete.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 323 0131, 323 3375, 323 9402

Fax 91 11 3234062, 91 11 3239399, 91 11 3239382

Telegrams: Manaksanstha (Common to all Offices)

Central Laboratory:	Telephone
Plot No. 20/9, Site IV, Sahibabad Industrial Area, SAHIBABAD 201010	8-77 00 32
Regional Offices:	
Central: Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	323 76 17
*Eastern: 1/14 CIT Scheme VII M, V.I.P. Road, Maniktola, CALCUTTA 700054	337 86 62
Northern: SCO 335-336, Sector 34-A, CHANDIGARH 160022	60 38 43
Southern · C.I.T. Campus, IV Cross Road, CHENNAI 600113	235 23 15
†Western · Manakalaya, E9 Behind Marol Telephone Exchange, Andheri (East) MUMBAI 400093	, 832 92 95
Branch Offices:	
'Pushpak', Nurmohamed Shaikh Marg. Khanpur, AHMEDABAD 380001	550 13 48
‡Peenya Industrial Area, 1st Stage, Bangalore - Tumkur Road, BANGALORE 560058	839 49 55
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	55 40 21
Plot No. 62-63, Unit VI, Ganga Nagar, BHUBANESHWAR 751001	40 36 27
Kalaikathir Buildings, 670 Avinashi Road, COIMBATORE 641037	21 01 41
Plot No. 43, Sector 16 A, Mathura Road, FARIDABAD 121001	8-28 88 01
Savitri Complex, 116 G. T. Road, GHAZIABAD 201001	8-71 19 96
53/5 Ward No. 29, R. G. Barua Road, 5th By-lane, GUWAHATI 781003	54 11 37
5-8-58C, L. N. Gupta Marg, Nampally Station Road, HYDERABAD 500001	20 10 83
E-52, Chitaranjan Marg, C-Scheme, JAIPUR 302001	37 29 25
117/418 B, Sarvodaya Nagar, KANPUR 208005	21 68 76
Seth Bhawan, 2nd Floor, Behind Leela Cinema, Naval Kishore Road, LUCKNOW 226001	23 89 23
Patliputra Industrial Estate, PATNA 800013	26 23 05
T. C. No. 14/1421, University P. O. Palayam, THIRUVANANTHAPURAM 695034	6 21 17
NIT Building, Second Floor, Gokulpat Market, NAGPUR 440010	52 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	32 36 35
*Sales Office is at 5 Chowringhee Approach, P. O. Princep Street,	27 10 65
CALCUTTA 700072	27 10 85
†Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400007	309 65 28
‡Sales Office is at 'F' Block, Unity Building, Narashimaraja Square, BANGALORE 560002	222 39 71